Printing date: 05.01.2023

*

Version: 1

Revision: 05.01.2023

1.1 I I Judici luci	ntifier	
Trade name: <u>G</u>	ALVA PROC	CAT MAT
Article number UFI: UUK5-E01 1.2 Relevant ide Application of t Aerosol coating Paint	DX-D00C-PA entified uses o	of the substance or mixture and uses advised against -
Manufacturer/S A.M.P.E.R.E. SY 3 rue Antoine Ba 95310 Saint-Oue	Supplier: (STEM lard - Z.I. du ' n-I'Aumône -	
1.4 Emergency reland : Nationa	telephone nu l Poisons Info	ble from: fds@amperesystem.com mber: UK : National Poisons Information Service - 0344 892 0111 rmation Centre - Beaumont Hospital - PO Box 1297 Beaumont Road 9 Dublin professionals-24/7) - +353 1 809 2166 (public, 8am - 10pm, 7/7)
SECTION 2	: Hazards i	dentification
		stance or mixture Regulation (EC) No 1272/2008
GHS)2 flame	
Aerosol 1		29 Extremely flammable aerosol. Pressurised container: May burst if heated.
Aerosol 1	H222-H22)9 environmer	nt
Aerosol 1 Aerosol 1 GHSC Aquatic Acute 1 Aquatic Chronic	H222-H22 09 environmer H400 21 H410	
Aerosol 1 GHS Aquatic Acute 1	H222-H22 09 environmer H400 21 H410	nt Very toxic to aquatic life.
Aerosol 1 Aerosol 1 GHSC Aquatic Acute 1 Aquatic Chronic	H222-H22 09 environmer H400 21 H410	nt Very toxic to aquatic life.
Aerosol 1 Aquatic Acute 1 Aquatic Chronic Aquatic Chronic GHS0 Eye Irrit. 2 STOT SE 3	H222-H22 09 environmer H400 1 H410 07 H319 H336	nt Very toxic to aquatic life. Very toxic to aquatic life with long lasting effects.
Aerosol 1 Aquatic Acute 1 Aquatic Chronic Aquatic Chronic GHSC Eye Irrit. 2 STOT SE 3 2.2 Label element Labelling accon The product is c	H222-H22 09 environmer H400 1 H410 07 H319 H336 ents rding to Regu lassified and I rams	nt Very toxic to aquatic life. Very toxic to aquatic life with long lasting effects. Causes serious eye irritation.
Aerosol 1 Aquatic Acute 1 Aquatic Chronic Aquatic Chronic Chronic GHSC Eye Irrit. 2 STOT SE 3 2.2 Label elemont Labelling accont The product is c Hazard pictogr	H222-H22 H222-H22 H400 1 H400 1 H410 H319 H336 H336 ents rding to Regulassified and lassified and lass	Not the second secon

GB

Safety data sheet according to 1907/2006/EC, Article 31

Printing date: 05.01.2023

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

	(Contd. of page 1)
	ns,C9,aromatics
propan-2-ol	
· Hazard sta	
	Extremely flammable aerosol. Pressurised container: May burst if heated.
H319	Causes serious eye irritation.
H336	May cause drowsiness or dizziness.
H410	Very toxic to aquatic life with long lasting effects.
	ary statements
P101	If medical advice is needed, have product container or label at hand.
P102	Keep out of reach of children.
P210	Keep away from heat, hot surfaces, sparks, open flames and other ignition sources. No smoking.
P211	Do not spray on an open flame or other ignition source.
P251	Do not pierce or burn, even after use.
P260	Do not breathe mist/vapours/spray.
P271	Use only outdoors or in a well-ventilated area.
P280	Wear protective gloves / eye protection.
P304+P340	IF INHALED: Remove person to fresh air and keep comfortable for breathing.
P305+P351	+P338 IF IN EYES: Rinse cautiously with water for several minutes. Remove contact lenses, if present and easy to do. Continue rinsing.
P312	Call a POISON CENTER/doctor if you feel unwell.
P403	Store in a well-ventilated place.
P410+P412	Protect from sunlight. Do not expose to temperatures exceeding 50 °C/122 °F.
P501	Dispose of contents/container in accordance with local/regional/national/international
	regulations.
· Additional	information:
EUH066 Re	peated exposure may cause skin dryness or cracking.
· 2.3 Other h	azards
· Results of l	PBT and vPvB assessment
• PBT: Not a	pplicable.

• **vPvB:** Not applicable.

SECTION 3: Composition/information on ingredients

· 3.2 Mixtures

· Description: Active substance with propellant

 Dangerous components: 		
CAS: 115-10-6 EINECS: 204-065-8 Reg.nr.: 01-2119472128-37	dimethyl ether Flam. Gas 1A, H220; Press. Gas (Liq.), H280	25-<50%
CAS: 7440-66-6 EINECS: 231-175-3 Reg.nr.: 01-2119467174-37	zinc powder -zinc dust (stabilized) Aquatic Acute 1, H400; Aquatic Chronic 1, H410	25-<50%
CAS: 67-64-1 EINECS: 200-662-2 Reg.nr.: 01-2119471330-49	Acetone Flam. Liq. 2, H225; Eye Irrit. 2, H319; STOT SE 3, H336, EUH066	10-<25%
CAS: 128601-23-0 EC number: 918-668-5 Reg.nr.: 01-2119455851-35	Hydrocarbons,C9,aromatics Flam. Liq. 3, H226; Asp. Tox. 1, H304; Aquatic Chronic 2, H411; STOT SE 3, H335-H336, EUH066	2.5-<10%
EC number: 905-588-0 Reg.nr.: 01-2119488216-32 01-2119486136-34	Reaction mass of ethylbenzene and xylene Flam. Liq. 3, H226; STOT RE 2, H373; Asp. Tox. 1, H304; Acute Tox. 4, H312; Acute Tox. 4, H332; Skin Irrit. 2, H315; Eye Irrit. 2, H319; STOT SE 3, H335	2.5-<10%
CAS: 67-63-0 EINECS: 200-661-7 Reg.nr.: 01-2119457558-25	propan-2-ol Flam. Liq. 2, H225; Eye Irrit. 2, H319; STOT SE 3, H336	1-<2.5%
	•	(Contd. on pag

Printing date: 05.01.2023

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

CAS: 57-55-6 EINECS: 200-338-0 Reg.nr.: 01-2119456809-23	Propylene glycol substance with a Community workplace exposure limit	(Contd. of page 2) 0.1-<1%
CAS: 7439-92-1 EINECS: 231-100-4	lead Repr. 1A, H360FD-H362; Aquatic Acute 1, H400 (M=1); Aquatic Chronic 1, H410 (M=10) Specific concentration limit: Repr. 1A; H360D: C ≥ 0.03 %	≥0.0025-<0.025%

· Additional information:

Aerosols and containers fitted with a solid atomizer containing substances or mixtures classified as hazardous by aspiration shall not be labelled for that hazard.

The text of the hazard statements mentioned here can be found in chapter 16.

SECTION 4: First aid measures

· 4.1 Description of first aid measures

- After inhalation: Supply fresh air; consult doctor in case of complaints.
- · After skin contact: Generally the product does not irritate the skin.
- After eye contact:

Rinse opened eye for several minutes under running water. If symptoms persist, consult a doctor.

- · After swallowing: Do not induce vomiting; call for medical help immediately.
- 4.2 Most important symptoms and effects, both acute and delayed
- No further relevant information available.
- · 4.3 Indication of any immediate medical attention and special treatment needed

No further relevant information available.

SECTION 5: Firefighting measures

- [•] 5.1 Extinguishing media
- Suitable extinguishing agents:
- Water haze

Fire-extinguishing powder

Carbon dioxide

Alcohol resistant foam

- · For safety reasons unsuitable extinguishing agents: Water with full jet
- 5.2 Special hazards arising from the substance or mixture No further relevant information available.
- 5.3 Advice for firefighters
- · Protective equipment: Mount respiratory protective device.

SECTION 6: Accidental release measures

· 6.1 Personal precautions, protective equipment and emergency procedures

Wear protective equipment. Keep unprotected persons away.

- 6.2 Environmental precautions:
- Do not allow product to reach sewage system or any water course.

Inform respective authorities in case of seepage into water course or sewage system.

Do not allow to enter sewers/ surface or ground water.

- 6.3 Methods and material for containment and cleaning up: Ensure adequate ventilation.
- Do not flush with water or aqueous cleansing agents
- · 6.4 Reference to other sections

See Section 7 for information on safe handling.

See Section 8 for information on personal protection equipment.

(Contd. on page 4)

GR

Printing date: 05.01.2023

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

See Section 13 for disposal information.

SECTION 7: Handling and storage

- •7.1 Precautions for safe handling Ensure good ventilation/exhaustion at the workplace.
- · Information about fire and explosion protection:
- Do not spray onto a naked flame or any incandescent material.
- Keep ignition sources away Do not smoke.
- Protect against electrostatic charges.
- Pressurised container: protect from sunlight and do not expose to temperatures exceeding 50°C, i.e. electric lights. Do not pierce or burn, even after use.

· 7.2 Conditions for safe storage, including any incompatibilities · Storage:

- · Requirements to be met by storerooms and receptacles: Store in a cool location.
- Observe official regulations on storing packagings with pressurised containers.
- · Information about storage in one common storage facility:
- Observe official regulations on storing packagings with pressurised containers.
- · Further information about storage conditions:
- Store in cool, dry conditions in well sealed receptacles.
- Protect from heat and direct sunlight.
- · 7.3 Specific end use(s) No further relevant information available.

SECTION 8: Exposure controls/personal protection

· 8.1 Control parameters

· Ingredient	ts with limit values that rec	quire monitoring at the workplace:			
115-10-6 dimethyl ether					
	ort-term value: 958 mg/m ³ , 500 ppm				
Lon	g-term value: 766 mg/m ³ , 40	00 ppm			
67-64-1 A	cetone				
	rt-term value: 3620 mg/m ³ , 1				
	g-term value: 1210 mg/m ³ , 5	500 ppm			
67-63-0 pr	*				
	rt-term value: 1250 mg/m ³ , 5				
	g-term value: 999 mg/m ³ , 40	00 ppm			
	ropylene glycol				
	g-term value: 474* 10** mg				
	al vapour and particulates **	particulates			
· DNELs					
	zinc powder -zinc dust (sta				
Oral	DNEL Long term-systemic	50 mg/kg bw/day (Worker)			
Dermal	DNEL Long term-systemic	5000 mg/kg bw/day (Consumer)			
		5000 mg/kg bw/day (Worker)			
Inhalative	DNEL Long term-systemic	2.5 mg/m3 (Consumer)			
		5 mg/m3 (Worker)			
67-64-1 A	67-64-1 Acetone				
Oral	DNEL Long term-systemic	62 mg/kg bw/day (Consumer)			
Dermal	DNEL Long term-systemic	62 mg/kg bw/day (Consumer)			
		186 mg/kg bw/day (Worker)			
		(Contd. on page 5)			

(Contd. of page 3)

GB

Safety data sheet according to 1907/2006/EC, Article 31

Printing date: 05.01.2023

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

IIIIIaialive	DNEL Acute-local		(Contd. or 2420 mg/m3 (Worker)	f pag
		stemic	200 mg/m3 (Consumer)	
	21 (22 20ng oom of		1210 mg/m3 (Worker)	
128601-23		9.arom		
Oral	•		11 mg/kg bw/day (Consumer)	
Dermal			11 mg/kg bw/day (Consumer)	
			25 mg/kg bw/day (Worker)	
Inhalative	DNEL Long term-sv	stemic	2 32 mg/m3 (Consumer)	
			100 mg/m3 (Worker)	
Reaction	mass of ethylbenzene	e and x		
Oral	•		1.6 mg/kg bw/day (Consumer)	
Dermal			108 mg/kg bw/day (Consumer)	
			180 mg/kg bw/day (Worker)	
Inhalative	DNEL Aigu-systémi	aue	174 mg/m3 (Consumer)	
	8,	1	289 mg/m3 (Worker)	
	DNEL Acute-local		289 mg/m3 (Worker)	
		stemic	14.8 mg/m3 (Consumer)	
	5,		77 mg/m3 (Worker)	
	DNEL Long term-lo	cal	174 mg/m3 (Consumer)	
	5		221 mg/m3 (Worker)	
67-63-0 pi	ropan-2-ol		6 ()	
Oral	-	stemic	26 mg/kg bw/day (Consumer)	
Dermal			319 mg/kg bw/day (Consumer)	
			888 mg/kg bw/day (Worker)	
Inhalative	DNEL Long term-sy	stemic	89 mg/m3 (Consumer)	
			500 mg/m3 (Worker)	
PNECs				
			ta hili taad)	
	zinc powder -zinc d	ust (str	LADILIZEO)	
7440-66-6	zinc powder -zinc d shwater			
7 440-66-6 PNEC Fre	shwater	20.6 n	mg/l (Undefind)	
7440-66-6 PNEC Fre PNEC Ma	shwater rine water	20.6 n 6.1 mg	mg/l (Undefind) ng/l (Undefind)	
7 440-66-6 PNEC Fre PNEC Ma PNEC Fre	shwater rine water shwater sediment	20.6 n 6.1 mg 118 m	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind)	
7440-66-6 PNEC Fre PNEC Ma PNEC Fre PNEC Soi	shwater rine water shwater sediment l	20.6 n 6.1 mg 118 m 56.6 n	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind)	
7440-66-6 PNEC Fre PNEC Ma PNEC Fre PNEC Soi PNEC Sev	shwater rine water shwater sediment l vage Treatment Plant	20.6 n 6.1 mg 118 m 56.6 n 52 mg	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind)	
7440-66-6 PNEC Fre PNEC Fre PNEC Soi PNEC Sev PNEC Ma	shwater rine water shwater sediment l vage Treatment Plant rine water sediment	20.6 n 6.1 mg 118 m 56.6 n 52 mg	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind)	
7440-66-6 PNEC Fre PNEC Ma PNEC Fre PNEC Soi PNEC Sev	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind)	
7440-66-6 PNEC Fre PNEC Ma PNEC Soi PNEC Sev PNEC Ma 67-64-1 A PNEC Ma	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone rine water	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n 1.06 n	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind) mg/l (Undefind)	
7440-66-6 PNEC Fre PNEC Fre PNEC Soi PNEC Sev PNEC Ma 67-64-1 A PNEC Ma PNEC Fre	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone rine water shwater sediment	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n 1.06 n 30.4 n	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind) mg/l (Undefind) mg/l(dry weight) (Undefind)	
7440-66-6 PNEC Fre PNEC Fre PNEC Soi PNEC Sev PNEC Ma 67-64-1 A PNEC Ma PNEC Fre PNEC Soi	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone rine water shwater sediment	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n 1.06 n 30.4 n 29.5 n	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind) mg/l(dry weight) (Undefind) mg/l(dry weight) (Undefind)	
7440-66-6 PNEC Fre PNEC Fre PNEC Soi PNEC Sev PNEC Ma 67-64-1 A PNEC Ma PNEC Fre PNEC Soi PNEC Soi	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone rine water shwater sediment l rine water sediment	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n 1.06 n 30.4 n 29.5 n 3.04 n	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind) mg/l(dry weight) (Undefind) mg/kg (Undefind) mg/l(dry weight) (Undefind)	
7440-66-6 PNEC Fre PNEC Fre PNEC Soi PNEC Sev PNEC Ma 67-64-1 A PNEC Ma PNEC Fre PNEC Soi PNEC Soi	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone rine water shwater sediment l rine water sediment mass of ethylbenzene	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n 1.06 n 30.4 n 29.5 n 3.04 n e and x	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind) mg/l(dry weight) (Undefind) mg/kg (Undefind) mg/l(dry weight) (Undefind)	
7440-66-6 PNEC Fre PNEC Fre PNEC Soi PNEC Sev PNEC Ma 67-64-1 A PNEC Ma PNEC Fre PNEC Soi PNEC Soi PNEC Ma	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone rine water shwater sediment l rine water sediment mass of ethylbenzene shwater	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n 1.06 n 30.4 n 29.5 n 3.04 n 29.5 n 3.04 n	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind) mg/l(dry weight) (Undefind) mg/kg (Undefind) mg/l(dry weight) (Undefind) mg/l(dry weight) (Undefind) xylene r mg/l (Undefind)	
7440-66-6 PNEC Fre PNEC Fre PNEC Soi PNEC Sev PNEC Ma 67-64-1 A PNEC Ma PNEC Fre PNEC Soi PNEC Ma PNEC Fre PNEC Fre PNEC Fre	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone rine water shwater sediment l rine water sediment mass of ethylbenzene shwater	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n 1.06 n 30.4 n 29.5 n 3.04 n e and x 0.327 0.327	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind) mg/l(Undefind) mg/kg (Undefind) mg/l(dry weight) (Undefind) mg/l(dry weight) (Undefind) mg/l(Undefind) xylene T mg/l (Undefind)	
7440-66-6 PNEC Fre PNEC Ma PNEC Soi PNEC Soi PNEC Ma 67-64-1 A PNEC Ma PNEC Fre PNEC Soi PNEC Ma PNEC Fre PNEC Fre PNEC Fre	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone rine water shwater sediment l rine water sediment mass of ethylbenzene shwater rine water shwater	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n 1.06 n 30.4 n 29.5 n 3.04 n 29.5 n 3.04 n 29.5 n 3.04 n	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind) mg/l(dry weight) (Undefind) mg/kg (Undefind) mg/l(dry weight) (Undefind) xylene V mg/l (Undefind) V mg/l (Undefind) H mg/l(dry weight) (Undefind)	
7440-66-6 PNEC Fre PNEC Fre PNEC Soi PNEC Sev PNEC Ma 67-64-1 A PNEC Ma PNEC Fre PNEC Soi PNEC Fre PNEC Fre PNEC Fre PNEC Fre PNEC Fre PNEC Soi	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone rine water shwater sediment l rine water sediment mass of ethylbenzene shwater rine water shwater	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n 1.06 n 30.4 n 29.5 n 3.04 n 29.5 n 3.04 n 29.5 z 0.327 0.327 12.64 2.31 n	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind) mg/l(dry weight) (Undefind) mg/kg (Undefind) mg/l(dry weight) (Undefind) xylene Mg/l (Undefind) Mg/l (Undefind) Mg/l (Undefind) Mg/l (Undefind) Mg/l (Undefind) Mg/l (Undefind)	
7440-66-6 PNEC Fre PNEC Fre PNEC Soi PNEC Sev PNEC Ma 67-64-1 A PNEC Ma PNEC Fre PNEC Soi PNEC Fre PNEC Fre PNEC Fre PNEC Fre PNEC Fre PNEC Soi PNEC Soi	shwater rine water shwater sediment l vage Treatment Plant rine water sediment cetone rine water shwater sediment l rine water sediment mass of ethylbenzene shwater rine water shwater	20.6 n 6.1 mg 118 m 56.6 n 52 mg 56.5 n 3.04 n 29.5 n 3.04 n e and x 0.327 0.327 12.64 2.31 n 6.58 n	mg/l (Undefind) ng/l (Undefind) ng/l(dry weight) (Undefind) mg/kg (Undefind) g/l (Undefind) mg/l(dry weight) (Undefind) mg/l(dry weight) (Undefind) mg/kg (Undefind) mg/l(dry weight) (Undefind) xylene Mg/l (Undefind) Mg/l (Undefind) Mg/l (Undefind) Mg/l (Undefind) Mg/l (Undefind) Mg/l (Undefind)	

Printing date: 05.01.2023

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

A Exposure controls Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Avoid contact with the eyes. Avoid contact with the eyes. Avoid contact with the eyes. Avoid contact with the eyes and skin. General ventilation Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A2-P2 Hand protection Wear gloves for the protection against chemicals according to EN 374 Wite gloves Solvent resistant gloves Solvent suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommend thickness of the material: ≥ 0.5 mm Predration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time are acceptab	dditional information: The lists valid during the making were used as basis.	(Contd. of page
Appropriate engineering controls No further data; see item 7. Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Avoid contact with the eyes. Avoid contact with the eyes and skin. General ventilation Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A2/P2 Hand protection Wear gloves for the protection against chemicals according to EN 374 Void contact with gloves Solvent resistant gloves Solvent resistant gloves Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove anterial For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splask guard we preformed thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splask guard we preforme gloves are aware that suitable gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material. The while the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has 		
Individual protection measures, such as personal protective equipment General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all solied and contaminated clothing Wash hands before breaks and at the end of work. Avoid contact with the eyes and skin. General ventilation Repiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A2/P2 Hand protection Wear gloves for the protection against chemicals according to EN 374 Solvent resistant gloves Solvent manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Pertation time of glovee material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greacer than 480 minutes. For short-erm or splash guard were recommend the same. We are aware that suitable gloves that offer this level of protection may not be available In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break trough time has to be found		
General protective and hygienic measures: Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Avoid contact with the eyes. Avoid contact with the eyes and skin. General ventilation Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A2/P2 Hand protection Wear gloves for the protection against chemicals according to EN 374 Solvent resistant gloves Solvent resistance of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves is not agood measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from whi the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eyefnee protection Safety glasses Destive Suit . (EN-1303		
Keep away from foodstuffs, beverages and feed. Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Avoid contact with the eyes. Avoid contact with the eyes. Repiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A2/P2 Hand protection Wear gloves for the protection against chemicals according to EN 374 Wear gloves for the protection against chemicals according to EN 374 Wear gloves for the protection against chemicals according to EN 374 Wear gloves Solvent resistant gloves Solvent resistant gloves Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the protective gloves and has to be gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Eye/face protection Safety glasses Eye/face protection Safety glasses Eye/face protection Safety glasses (Eye) 136		
Immediately remove all soiled and contaminated clothing Wash hands before breaks and at the end of work. Avoid contact with the eyes. Avoid contact with the eyes and skin. General ventilation Respiratory protection Use suitable respiratory protective device in case of insufficient ventilation. Filter A2/2 Hand protection Wear gloves for the protection against chemicals according to EN 374 Work protective gloves Solvent resistant gloves Solvent resistant gloves Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of glove The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from whit the gloves are made. The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Dot protections Safety glasses Dot protections Safety glasses Dot protections Safety glasses Dot protections Hu skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&&EN 180 1368K; EN13034-6).		
Wash hands before breaks and at the end of work. Avoid contact with the eyes. Avoid contact with the eyes and skin. General ventilation Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A2/P2 Hand protection Wear gloves for the protection against chemicals according to EN 374 Wear gloves for the protection against chemicals according to EN 374 Solvent resistant gloves Solvent resistant gloves The selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves is not a good measure of the resistance of the gloves are made. The exact breakthrough time has to be found out by the manufacturer of the protective gloves and has to be observed. Everface protection Safety glasses Dightly sealed goggles Solver seal: LY (SOL 13688; EN 13034-6). Full skin covering antistatic, ch		
Avoid contact with the eyes. Avoid contact with the eyes and skin. General ventilation Repiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A2P2 Hand protection Wear gloves for the protection against chemicals according to EN 374 Wear gloves for the protection against chemicals according to EN 374 Wear gloves for the protection against chemicals according to EN 374 Wear gloves material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the glove material on consideration of the penetration times, rates of number marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from whit the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Evoface protection Safety glasses Dightly scaled goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&&EN NEO 1368&E, EN3034-6).		
Avoid contact with the eyes and skin. General ventilation Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A2/P2 Hand protection Wear gloves for the protection against chemicals according to EN 374 <i>Wear</i> gloves for the protection against chemicals according to EN 374 <i>Wear</i> gloves for the protection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be available In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Edoy protection Suffy glasses Edoy protection Suffy glasses Exact break Inogaintistatic, chemical and oil resistant		
Respiratory protection: Use suitable respiratory protective device in case of insufficient ventilation. Filter A2/P2 Hand protection Wear gloves for the protection against chemicals according to EN 374		
Use suitable respiratory protective device in case of insufficient ventilation. Filter A2/P2 Hand protection Wear gloves for the protection against chemicals according to EN 374	General ventilation	
Filter A2/P2 Hand protection Wear gloves for the protection against chemicals according to EN 374 Wear gloves for the protection against chemicals according to EN 374 Solvent resistant gloves Solvent resistant gloves The selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the protective glovers and has to be gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. Eye/face protection Safety glasses Digital glasses Digital glasses Digital glasses Digital sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN3040&EN ISO 13688; EN13034-6).	Respiratory protection:	
Hand protection Wear gloves for the protection against chemicals according to EN 374 Wear gloves for the protection against chemicals according to EN 374 Wear gloves for the protective gloves Solvent resistant gloves Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the protective gloves and has to be gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. Eye/face protection Safety glasses Selection Safety glasses Digntly sealed goggles Hody protection Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN3042EN ISO 13688; EN13034-6).	Jse suitable respiratory protective device in case of insufficient ventilation.	
Wear gloves for the protection against chemicals according to EN 374 Protective gloves Solvent resistant gloves Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradation Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be available In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Tightly sealed goggles Mody protection: Use protective suit, (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&&EN ISO 13688; EN13034-6).	ilter A2/P2	
Very Protective gloves Solvent resistant gloves Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be available In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from whice the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eyoface protection Safety glasses Digitive selected Safety glasses Digitive selected Safety glasses Digitive selected Safety glasses Digitive selected Safety glasses Digitive selected Safety slasses Digitive selected Safety slas	land protection	
Solvent resistant gloves Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves hat offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Doty protection Safety glasses Doty protection : Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).	Vear gloves for the protection against chemicals according to EN 374	
Solvent resistant gloves Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves hat offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Doty protection Safety glasses Doty protection : Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).	μ.	
Solvent resistant gloves Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves hat offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break through time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Doty protection Safety glasses Doty protection : Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).	W? Protective gloves	
Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: $\geq 0.5 \text{ mm}$ Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
Selection of the glove material on consideration of the penetration times, rates of diffusion and the degradatic Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: $\geq 0.5 \text{ mm}$ Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).	alvent registert glaves	
Material of gloves The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be available In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the material from which the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		on and the degradatio
The selection of the suitable gloves does not only depend on the material, but also on further marks of quality and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		on and the degradatio
and varies from manufacturer to manufacturer. As the product is a preparation of several substances, the resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		ther marks of quality
resistance of the glove material can not be calculated in advance and has therefore to be checked prior to the application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be available In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Display protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
application. Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from whice the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
Nitrile rubber, NBR Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from whice the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		encence prior to the
Recommended thickness of the material: ≥ 0.5 mm Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be availabl In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
Penetration time of glove material For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be available. In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
For continuous contact we recommend gloves with breakthrough time of at least 240 minutes, with the preference given to a breakthrough time greater than 480 minutes. For short-term or splash guard we recommend the same. We are aware that suitable gloves that offer this level of protection may not be available in that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from whice the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
recommend the same. We are aware that suitable gloves that offer this level of protection may not be available In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from whice the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		nutes, with the
In that case, a shorter breakthrough time are acceptable as long as the procedures governing maintenance and timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from whice the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).	reference given to a breakthrough time greater than 480 minutes. For short-term or spla	sh guard we
 timely replacement are followed. The thickness of the gloves is not a good measure of the resistance of the gloves against a chemical substance, because this depends on the exact composition of the material from whice the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Dightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6). 	ecommend the same. We are aware that suitable gloves that offer this level of protection	n may not be availabl
 gloves against a chemical substance, because this depends on the exact composition of the material from which the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6). 		
 the gloves are made. The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6). 		
The exact break trough time has to be found out by the manufacturer of the protective gloves and has to be observed. Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		ne material from which
observed. Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
 Eye/face protection Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6). 		oves and has to be
Safety glasses Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
Tightly sealed goggles Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).	arery grasses	
Body protection: Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).	Tightly sealed goggles	
Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
Use protective suit. (EN-13034/6) Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).	ody protection:	
Full skin covering antistatic, chemical and oil resistant clothing and safety shoes are recommended. (EN1149 EN340&EN ISO 13688; EN13034-6).		
EN340&EN ISO 13688; EN13034-6).		mmended. (EN1149
		(
		ontamination.

Printing date: 05.01.2023

*

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

(Contd. of page 6)

9.1 Information on basic physical and chemical pr	operties
General Information Physical state	Aerosol
Colour:	Grey
Odour:	Characteristic
Odour threshold:	Not determined.
Melting point/freezing point:	Undetermined.
Boiling point or initial boiling point and boiling	
range	-24.8 °C (115-10-6 dimethyl ether)
Flammability	Not applicable.
Lower and upper explosion limit	
Lower:	1 Vol % (128601-23-0 Hydrocarbons,C9,aromatics)
Upper:	13 Vol % (67-64-1 Acetone)
Flash point:	-41 °C (115-10-6 dimethyl ether)
Ignition Temperature	465 °C
pH	Mixture is non-polar/aprotic.
Viscosity:	
Kinematic viscosity	Not determined.
Dynamic:	Not determined
Solubility	Not missible or diff
water: Partition coefficient n-octanol/water (log value)	Not miscible or difficult to mix. Not determined.
Partition coefficient n-octanol/water (log value) Vapour pressure at 20 °C:	Solo hPa
v apour pressure at 20 °C: Density and/or relative density	5500 III a
Density and/or relative density Density at 20 °C:	1.04 g/cm ³
Relative density	Not determined.
Vapour density	Not determined.
9.2 Other information	
Appearance: Form:	Aerosol
rorm: Important information on protection of health and	
environment, and on safety.	-
Auto-ignition temperature:	Product is not selfigniting.
Explosive properties:	Product is not explosive. However, formation of
· · · ·	explosive air/vapour mixtures are possible.
Solvent content:	· · · ·
Organic solvents:	64.4 %
Solids content:	34.2 %
Change in condition	
Evaporation rate	Not applicable.
Information with regard to physical hazard classe	'S
Explosives	Void
Flammable gases	Void
Aerosols	Extremely flammable aerosol. Pressurised container:
	May burst if heated.
Oxidising gases	Void
Gases under pressure	Void
Flammable liquids	Void
Flammable solids	Void
Self-reactive substances and mixtures	Void
Pyrophoric liquids	Void
Pyrophoric solids	Void
Self-heating substances and mixtures	Void
Substances and mixtures, which emit flammable	
gases in contact with water	Void

Printing date: 05.01.2023

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

		(Contd. of page 7)
· Oxidising liquids	Void	
• Oxidising solids	Void	
· Organic peroxides	Void	
· Corrosive to metals	Void	
· Desensitised explosives	Void	

SECTION 10: Stability and reactivity

· 10.1 Reactivity No further relevant information available.

· 10.2 Chemical stability

• Thermal decomposition / conditions to be avoided: No decomposition if used according to specifications.

• 10.3 Possibility of hazardous reactions No dangerous reactions known.

· 10.4 Conditions to avoid No further relevant information available.

 \cdot 10.5 Incompatible materials: No further relevant information available.

· 10.6 Hazardous decomposition products: No dangerous decomposition products known.

SECTION 11: Toxicological information

· 11.1 Information on hazard classes as defined in Regulation (EC) No 1272/2008

• Acute toxicity Based on available data, the classification criteria are not met.

7440-66-6	zinc powd	er -zinc dust (stabilized)		
Oral	Dral LD50 >2000 mg/kg (Rat)			
Inhalative	LC50 (4h)	>5.4 mg/l (Rat)		
67-64-1 A	cetone			
Oral	LD50	5800 mg/kg (Rat) (Acute Oral Toxicity)		
Dermal	LD50	7800 mg/kg (Rabbit)		
Inhalative	LC50 (4h)	>20 mg/l (Rat)		
128601-23	-0 Hydroca	arbons,C9,aromatics		
Oral	LD50	3492 mg/kg (Rat)		
Dermal	LD50	>3160 mg/kg (Rabbit)		
Inhalative	LC50 (4h)	>6193 mg/l (Rat) (Acute Inhalation Toxicity)		
Reaction 1	nass of eth	ylbenzene and xylene		
Oral	LD50	3523 mg/kg (Rat)		
Dermal	LD50	12126 mg/kg (Rabbit)		
Inhalative	LC50 (4h)	29000 mg/l (Rat)		
67-63-0 propan-2-ol				
Oral	LD50	5840 mg/kg (Rat)		
Dermal	LD50	13900 mg/kg (Rabbit)		
Inhalative	LC50 (4h)	>25 mg/l (Rat)		
	LC50	>25 mg/L (Rat) (Acute Inhalation Toxicity)		
		tion Based on available data, the classification criteria are not met.		
Serious ev	e damage/i	rritation Causes serious eye irritation.		

• Carcinogenicity Based on available data, the classification criteria are not met.

• **Reproductive toxicity** Based on available data, the classification criteria are not met.

• STOT-single exposure May cause drowsiness or dizziness.

· STOT-repeated exposure Based on available data, the classification criteria are not met.

· Aspiration hazard Based on available data, the classification criteria are not met.

(Contd. on page 9)

GB

Printing date: 05.01.2023

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

· 11.2 Information on other hazards

• Endocrine disrupting properties None of the ingredients is listed.

SECTION 12: Ecological information

· 12.1 Toxicity

*

· A questio toxicity					
· Aquatic toxicity					
-	7440-66-6 zinc powder -zinc dust (stabilized)				
EC50	354 ug/l (dap)				
· · ·	178 ug/l (Crustaceeen-Palaemon elegans)				
NOEC (72h)	9 mg/l (Ceratophyllum demersum)				
	0.017 mg/l (Pseudokirchneriella subcapitata)				
NOEC (72h)	72.9 ug/l (Pseudokirchneriella subcapitata)				
NOEC (28 days)					
EC10 (21 days)	59.2 ug/l (Daphnia magna)				
EC10 (72h)	27.3 ug/l (Algae)				
EC50 (72h)	0.17 mg/l (Selenastrum capricornatum)				
LC50 (96h)	0.41 mg/l (Oncorhynchus mykiss)				
EC50 (48h)	1 mg/l (Daphnia magna)				
EC50 (96h)	0.527 mg/l (Algae)				
LC50	238-269 ug/l (fi2)				
67-64-1 Acetone					
EC50	8800 mg/l (Daphnia magna)				
	8300 mg/l (Fish)				
128601-23-0 Hy	drocarbons,C9,aromatics				
NOELR (72h)	1 mg/l (Pseudokirchneriella subcapitata)				
EL50 (48h)	3.2 mg/l (Daphnia magna)				
LL50 (96h)	9.2 mg/l (Oncorhynchus mykiss)				
Reaction mass o	f ethylbenzene and xylene				
NOEC	1.3 mg/l (Fish)				
NOEC (7 days)	0.96 mg/l (Daphnia magna)				
NOEC (72h)	0.44 mg/l (Algae)				
NOEC (28 days)	16 mg/l (Bacteria)				
LC50 (96h)	8.9-16.4 mg/l (Pimephales promelas)				
EC50 (48h)	3.2-9.5 mg/l (Daphnia magna)				
67-63-0 propan-	67-63-0 propan-2-ol				
EC50	>100 mg/l (Bacteria)				
LOEC (8 days)	1000 mg/l (Algae)				
LC50 (96h)	9640 mg/l (Pimephales promelas)				
LC50 (24h)	9714 mg/l (Daphnia magna)				
 12.3 Bioaccumul 12.4 Mobility in 12.5 Results of P PBT: Not applica 	 12.2 Persistence and degradability Not easily biodegradable 12.3 Bioaccumulative potential No further relevant information available. 12.4 Mobility in soil No further relevant information available. 12.5 Results of PBT and vPvB assessment PBT: Not applicable. vPvB: Not applicable. 				
1 1		(Contd. on page 10)			

(Contd. of page 8)

GB

Printing date: 05.01.2023

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

• 12.6 Endocrine disrupting properties

The product does not contain substances with endocrine disrupting properties.

· 12.7 Other adverse effects

· Remark: Very toxic for fish

· Additional ecological information:

· General notes:

Water hazard class 2 (German Regulation) (Self-assessment): hazardous for water

Do not allow product to reach ground water, water course or sewage system.

Danger to drinking water if even small quantities leak into the ground.

Also poisonous for fish and plankton in water bodies.

Very toxic for aquatic organisms

SECTION 13: Disposal considerations

· 13.1 Waste treatment methods

· Recommendation

Must not be disposed together with household garbage. Do not allow product to reach sewage system.

· European	waste	catalogue
------------	-------	-----------

HP3 Flammable

HP4 Irritant - skin irritation and eye damage

HP14 Ecotoxic

· Uncleaned packaging:

• Recommendation: Disposal must be made according to official regulations.

14.1 UN number or ID number	UN1950
ADR, ADN, IMDG, IATA	0661010
14.2 UN proper shipping name	
· ADR, ADN · IMDG	UN1950 AEROSOLS, ENVIRONMENTALLY
	HAZARDOUS AEROSOLS, MARINE POLLUTANT
· IATA	AEROSOLS, MARINE FOLLOTANT AEROSOLS, flammable
	ALKOSOLS, Hammaole
14.3 Transport hazard class(es)	
ADR	
Class	2 5F Gases.
Label	2.1
ADN ADN/R Class:	2 5F
	2 51
IMDG	

(Contd. of page 9)

Printing date: 05.01.2023

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

	(Contd. of page
Label	2.1
ΙΑΤΑ	
2	
Class	2.1 Gases.
Label	2.1 Gases. 2.1
14.4 Packing group	
ADR, IMDG, IATA	Void
14.5 Environmental hazards:	Product contains environmentally hazardous
14.5 Environmental hazards.	substances: Hydrocarbons,C9,aromatics
Marine pollutant:	Yes
F	Symbol (fish and tree)
Special marking (ADR):	Symbol (fish and tree)
14.6 Special precautions for user	Warning: Gases.
Hazard identification number (Kemler code)	
EMS Number:	F-D,S-U
Stowage Code	SW1 Protected from sources of heat.
	SW22 For AEROSOLS with a maximum capacity of
	litre: Category A. For AEROSOLS with a capacity
	above 1 litre: Category B. For WASTE AEROSOLS: Category C, Clear of living quarters.
Segregation Code	SG69 For AEROSOLS with a maximum capacity of 1
Segregation Code	litre:
	Segregation as for class 9. Stow "separated from" clas
	1 except for division 1.4.
	For AEROSOLS with a capacity above 1 litre:
	Segregation as for the appropriate subdivision of class
	2. For WASTE AEROSOLS:
	Segregation as for the appropriate subdivision of class
	2.
14.7 Maritime transport in bulk according to	
instruments	Not applicable.
Transport/Additional information:	~~
ADR	
Limited quantities (LQ)	1L
Excepted quantities (EQ)	Code: E0
Zacepreu quantities (EQ)	Not permitted as Excepted Quantity
Transport category	2
Tunnel restriction code	D
IMDG	
Limited quantities (LQ)	1L
• Excepted quantities (EQ)	Code: E0
	Not permitted as Excepted Quantity
UN "Model Regulation":	UN 1950 AEROSOLS, 2.1, ENVIRONMENTALLY
2	HAZARDOUS

(Contd. on page 12)

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

Printing date: 05.01.2023

SECTION 15: Regulatory information
· 15.1 Safety, health and environmental regulations/legislation specific for the substance or mixture
· Directive 2012/18/EU
· Named dangerous substances - ANNEX I None of the ingredients is listed.
• Seveso category E1 Hazardous to the Aquatic Environment
P3a FLAMMABLE AEROSOLS
Qualifying quantity (tonnes) for the application of lower-tier requirements 100 t
• Qualifying quantity (tonnes) for the application of upper-tier requirements 200 t • REGULATION (EC) No 1907/2006 ANNEX XVII Conditions of restriction: 3, 63, 72
· Regulation (EU) No 649/2012
7439-92-1 lead Annex I Part 1
• DIRECTIVE 2011/65/EU on the restriction of the use of certain hazardous substances in electrical and electronic equipment – Annex II
None of the ingredients is listed.
· REGULATION (EU) 2019/1148
 Annex I - RESTRICTED EXPLOSIVES PRECURSORS (Upper limit value for the purpose of licensing under Article 5(3))
None of the ingredients is listed.
· Annex II - REPORTABLE EXPLOSIVES PRECURSORS
67-64-1 Acetone
· Regulation (EC) No 273/2004 on drug precursors
67-64-1 Acetone 3
• Regulation (EC) No 111/2005 laying down rules for the monitoring of trade between the Community and third countries in drug precursors
67-64-1 Acetone 3
· National regulations:
· Breakdown regulations:
Class Share in %
NK 50-<75
· VOC-CH 64.40 %
· VOC-EU 669.8 g/l · Danish MAL Code 5-3
• 15.2 Chemical safety assessment: A Chemical Safety Assessment has not been carried out.

SECTION 16: Other information

This information is based on our present knowledge. However, this shall not constitute a guarantee for any specific product features and shall not establish a legally valid contractual relationship.

· Relevant phrases

- H220 Extremely flammable gas.
- H225 Highly flammable liquid and vapour.
- H226 Flammable liquid and vapour.
- H280 Contains gas under pressure; may explode if heated.
- H304 May be fatal if swallowed and enters airways.
- H312 Harmful in contact with skin.
- H315 Causes skin irritation.
- H319 Causes serious eye irritation.
- H332 Harmful if inhaled.
- H335 May cause respiratory irritation.

Printing date: 05.01.2023

Version: 1

Revision: 05.01.2023

Trade name: GALVA PROCAT MAT

	(Contd. of page 1
H336 May cause drowsiness or dizziness.	
H360FD May damage fertility. May damage the unborn child.	
H362 May cause harm to breast-fed children.	
H373 May cause damage to organs through prolonged or repeated exposure.	
H400 Very toxic to aquatic life.	
H410 Very toxic to aquatic life with long lasting effects.	
H411 Toxic to aquatic life with long lasting effects.	
EUH066 Repeated exposure may cause skin dryness or cracking.	
Classification according to Regulation (EC) No 1272/2008	· · · · · · · · · · · · · · · · · · ·
Physical and chemical properties: The classification is based on the results of the n	
hazards, Environmental hazards: The method of classification of mixtures based or	n the constituents of the
mixture (sum formula).	
[•] Department issuing SDS: Research & Development	
• Date of previous version: 08.08.2022	
· Abbreviations and acronyms:	
RID: Règlement international concernant le transport des marchandises dangereuses par chemin de fer	(Regulations Concerning the
International Transport of Dangerous Goods by Rail)	(888
ICAO: International Civil Aviation Organisation	
ADR: Accord relatif au transport international des marchandises dangereuses par route (European Agr	eement Concerning the
International Carriage of Dangerous Goods by Road)	
IMDG: International Maritime Code for Dangerous Goods	
IATA: International Air Transport Association	
GHS: Globally Harmonised System of Classification and Labelling of Chemicals	
EINECS: European Inventory of Existing Commercial Chemical Substances ELINCS: European List of Notified Chemical Substances	
CAS: Chemical Abstracts Service (division of the American Chemical Society)	
MAL-Code: Måleteknisk Arbejdshygiejnisk Luftbehov (Regulation for the labeling concerning inhalat	tion hazards. Denmark)
DNEL: Derived No-Effect Level (UK REACH)	
PNEC: Predicted No-Effect Concentration (UK REACH)	
LC50: Lethal concentration, 50 percent	
LD50: Lethal dose, 50 percent	
PBT: Persistent, Bioaccumulative and Toxic	
vPvB: very Persistent and very Bioaccumulative	
Flam. Gas 1A: Flammable gases – Category 1A	
Aerosol 1: Aerosols – Category 1	
Press. Gas (Liq.): Gases under pressure – Liquefied gas Flam. Liq. 2: Flammable liquids – Category 2	
Flam. Liq. 2. Flammable liquids – Category 3	
Acute Tox. 4: Acute toxicity – Category 4	
Skin Irrit. 2: Skin corrosion/irritation – Category 2	
Eye Irrit. 2: Serious eye damage/eye irritation – Category 2	
Repr. 1A: Reproductive toxicity – Category 1A	
STOT SE 3: Specific target organ toxicity (single exposure) – Category 3	
STOT RE 2: Specific target organ toxicity (repeated exposure) – Category 2	
Asp. Tox. 1: Aspiration hazard – Category 1	
Aquatic Acute 1: Hazardous to the aquatic environment - acute aquatic hazard – Category 1	
Aquatic Chronic 1: Hazardous to the aquatic environment - long-term aquatic hazard – Category 1	
Aquatic Chronic 2: Hazardous to the aquatic environment - long-term aquatic hazard – Category 2	
• * Data compared to the previous version altered. *	
IMER	

DISCLAIMER

The information contained in this sheet comes from reliable sources. It has been drawn up based on our knowledge at the time of the most recent update, as indicated. This information is intended as an aid to the user and should not be considered as a guarantee.

Conditions or methods of handling, storage, use or disposal of the product are outside our control, and we may not be held responsible for any loss, damage or expenses incurred as a result of, or in connection with, the latter.

safety, and the protection of human health and the environment.

All substances or mixtures can present unknown dangers and must be used with caution. We cannot guarantee that all dangers have been set out in an exhaustive manner. This sheet has been drawn up for, and must be used for, this product only. If the product is used as a component in another product, the information given with it may not be applicable. This sheet does not under any circumstances exempt the user from complying with all laws, regulations and administrative requirements related to the product, health and